

White Kraft Paper

Quality Specification

validity: 2026-01-01~2026-12-31

Item	GSM	Bulk	Smoothness		Burst Index	Folding resistance	Tear Index	Water Uptake Value	Moisture
Unit	g/m ²	cm ³ /g	Front(S)	Back(s)	kPa.m ² /g	Times(CD)	mN.m ² /g(MD)	g/m ²	%
White Kraft paer	80±4	1.20±0.05	≥ 30	≥ 28	≥ 2.2	≥ 20	≥ 6.0	30±10	4.5-8.0
	93±4	1.20±0.05	≥ 30	≥ 28	≥ 2.2	≥ 20	≥ 6.0	30±10	4.5-8.0
	97±4	1.20±0.05	≥ 30	≥ 28	≥ 2.2	≥ 20	≥ 6.0	30±10	4.5-8.0
	110±5	1.20±0.05	≥ 30	≥ 28	≥ 2.2	≥ 20	≥ 6.0	30±10	4.5-8.0
	117±5	1.20±0.05	≥ 28	≥ 24	≥ 2.1	≥ 20	≥ 6.0	30±10	4.5-8.0
	127±5	1.20±0.05	≥ 28	≥ 24	≥ 2.1	≥ 20	≥ 6.0	30±10	4.5-8.0
	137±5	1.20±0.05	≥ 28	≥ 24	≥ 2.1	≥ 20	≥ 6.0	30±10	4.5-8.0
	147±5	1.20±0.05	≥ 28	≥ 24	≥ 2.1	≥ 20	≥ 6.0	30±10	4.5-8.0
	175±6	1.20±0.05	≥ 24	≥ 20	≥ 1.9	≥ 20	≥ 6.0	30±10	4.5-8.0
	190±6	1.20±0.05	≥ 24	≥ 20	≥ 1.9	≥ 20	≥ 6.0	30±10	4.5-8.0
	200±7	1.20±0.05	≥ 24	≥ 20	≥ 1.9	≥ 20	≥ 6.0	30±10	4.5-8.0
	230±7	1.20±0.05	≥ 24	≥ 20	≥ 1.9	≥ 20	≥ 6.0	30±10	4.5-8.0
	290±10	1.20±0.05	≥ 15	≥ 12	≥ 1.6	≥ 20	≥ 6.0	30±10	4.5-8.0
	330±10	1.20±0.05	≥ 15	≥ 12	≥ 1.6	≥ 20	≥ 6.0	30±10	4.5-8.0

Above data is just for reference.